



TECHNICAL DATA

VELOUR 3165 BACK TO BACK

Construction Characteristics

Construction
Base Material

Width tape : < 50mm
 ≥ 50 mm
 ≥ 100 mm

Weight

Usage Characteristics

Peel Strength with VELCRO® brand Hook 088 *

Shear Strength with VELCRO® brand Hook 088 *

Peel Strength after 200 cycles with VELCRO® brand Hook 088*

Shear Strength after 200 cycles with VELCRO® brand Hook 088 *

Breaking Strength *

Washing resistance (40°C) **

Colourfastness to washing ISO 105 sec/CO3
Colourfastness to dry cleaning ISO 105 sec/DO1
Colourfastness to rubbing ISO 105 sec/X12
Colourfastness to water ISO 105 sec/EO1
Colourfastness to sea water ISO 105 sec/EO2
Colourfastness to light ISO 105 sec/BO2
Colourfastness to perspiration ISO 105 sec/EO4

* Internal norm of VESA

** Data indicated considers dry tape tested after washing cycle

Knitted
Polyamide

Nominal ± 1 mm
Nominal ± 1,5 mm
Nominal ± 2 mm

635 g/m² ± 10 %

Average 1,0 N/cm
Minimum value 0,7 N/cm

Average 8,0 N/cm²
Minimum value 4,7 N/cm²

Average 0,8 N/cm
Minimum value 0,4 N/cm

Average 6,3 N/cm²
Minimum value 3,6 N/cm²

Mínimum 126 N/cm

Minimum 5 N/cm (delamination force)

4 minimum
4 minimum
4 minimum
4 minimum
4 minimum
5 minimum
4 minimum

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

Elaborado: J.C. Lima

Revisado: E. Ducet

Autorizado: J. Camarillo

Fecha: 23.01.14

ANEXO: IDT – 605-B

FTP 307 Versión 5